

PRODUCT SPECIFICATION SHEET multiprop 3230

PE/PP Regrind

multiprop 3230

Description

PE/PP- Regrind from bottles caps

Properties

| | |
|-------------|--------------------------|
| Application | injection moulding |
| Grain size | 10 mm (max. 5 % > 10 mm) |

Packing

Big Bag on non-returnable pallet
H x W x D: ca. 2,50 m x 1,06 m x 1,06 m
weight app. 1200 kg per Big Bag

Purity

| | |
|---|---------------|
| Melt flow index MFR at 190°C/5kg (DIN ISO 1133) | 3-20 g/10 min |
| Surface humidity | ≤ 1,0 % |
| Other (Dichte > 1,0 g/cm³) | ≤ 1,0 % |
| Bulk density | ≥ 275 kg/m³ |

Our products are manufactured with the utmost care and are subject to regular quality controls. Nevertheless, slight material variations can occur.

All data stated on our product information are average values and are based on our current knowledge and experience. They do not release the user from careful examination when applying and using our products, due to the variety of possible influences.

Legally binding commitments of certain properties for precise applications cannot be made from our stipulations. Any property rights as well as existing laws and regulations are to be observed by the receiver respectively processor of our products, on individual responsibility.

Our products are not suitable for the application in the context of the act (EC) no. 282/2008. In the following, our general conditions of sale are valid.

issue: 20.09.2013

